



# Technical Data Sheet

## Apcoflex<sup>®</sup> N686

Medium ACN, High Viscosity Nitrile Rubber

### CHEMICAL DESCRIPTION

Apcoflex<sup>®</sup> N686 is a cold polymerized, medium ACN containing acrylonitrile butadiene co-polymer, It contains non-staining antioxidant.

CAS No.: 9003-18-3

### APPLICATIONS

Apcoflex<sup>®</sup> N686 is a high viscosity highly suitable for the manufacture of products where excellent thermal, abrasion and fuel resistances are desired.

It is also recommended for applications in the manufacture of Printing & Industrial rollers, Hoses & Tubings, Jointing Sheets, Footwear, Cable & Wires where good physicals are desired

### TYPICAL PROPERTIES

Bound Acrylonitrile, %	33
Mooney Viscosity, ML1+4(100°C)	60
Ash, %	0.33
Volatiles, %	0.42
Specific gravity	0.98

### SAFETY AND HANDLING

Apcoflex<sup>®</sup> N686 may contain traces of residual monomers, which may be released during processing at high temperatures. Therefore adequate ventilation should be employed in the processing areas.

### PACKAGING AND SHELF-LIFE

These bales are wrapped in plastic films and packed in poly-coated woven sacks.

Approx. Dimensions (in): 28x14x5.5 (when packed) for 25 kg

28x14x7.0 (when packed) for 35 kg

Weight, kg 25 OR 35 kg net (when packed)

Recommended to store in original packaging, away from direct sources of heat and sunlight. These bales will have a minimum of 24 months shelf-life under good storage practices.

PDS-N686-17-02

apcotex industries limited

Email  : info@apcotex.com

Web  : www.apcotex.com

**Disclaimer :** These suggestions and data are based on information that we believe to be reliable. They are given for information only and in good faith, but conditions and methods of use of our products are beyond our control. Apcotex recommends that the user determine the suitability of our materials and suggestions before using them on a commercial scale