



## Apcoflex<sup>®</sup> N684

Medium ACN, Medium Viscosity Nitrile Rubber

### CHEMICAL DESCRIPTION

Apcoflex<sup>®</sup> N684 is a cold polymerized, medium ACN containing acrylonitrile butadiene co-polymer.

It contains non-staining antioxidant.

CAS N°: 9003-18-3

### APPLICATIONS

Apcoflex<sup>®</sup> N684 is an easy processing, medium viscosity grade suitable for injection, compression moulding as well as extrusion goods in Industrial and Automotive sectors for products such as Seals, O-Rings, Bellows, Diaphragms and Fuel Tubes etc. where high flow is desired.

The other recommended applications of this grade are in the manufacture of Rubber Rollers, Jointing Sheets, LPG Tubing, Footwear, Cable & Wires etc.

### PRODUCT SPECIFICATIONS

PROPERTY	LIMITS
Volatile Matter,%	0.7 Max.
Mooney Viscosity, ML 1+4 @ 100°C, MU	35 - 45
Ash Content,%	0.5 Max.
Bound Acrylonitrile, %	32 - 35

### SAFETY AND HANDLING

Apcoflex<sup>®</sup> N684 may contain traces of residual monomers, which may be released during processing at high temperatures. Therefore adequate ventilation should be employed in the processing areas.

### PACKAGING AND SHELF-LIFE

These bales are wrapped in plastic films and packed in woven sacks.

Appx. Dimensions (in): 28x14x5.5 (when packed) for 25 kg


28x14x7.0 (when packed) for 35 kg


Weight, kg 35 kg net (when packed)

Recommended to store in original packaging, away from direct sources of heat and sunlight. These bales will have a minimum of 24 months shelf-life under good storage practices.

PDS-N684-18-09

apcotex industries limited

Email  : info@apcotex.com

Web  : www.apcotex.com

**Disclaimer** : These suggestions and data are based on information that we believe to be reliable. They are given for information only and in good faith, but conditions and methods of use of our products are beyond our control. Apcotex recommends that the user determine the suitability of our materials and suggestions before using them on a commercial scale.