



# Technical Data Sheet

## Apcoflex<sup>®</sup> NL238

Anionic aqueous dispersion of a Butadiene-Acrylonitrile copolymer

### KEY ADVANTAGES

- Contains non-staining antioxidant
- Excellent Fuel & solvent Resistance
- Excellent gloss development, moderate tackiness
- Excellent Film strength

### TYPICAL PROPERTIES

Type	Butadiene- acrylonitrile copolymer
pH	9
Total Solid, %	50
Brookfield Viscosity, cps	90
CAS No.	9003 -18-3
Mechanical Stability	Good

### APPLICATIONS

- Binder in Cork Sheets
- Binder in Gaskets
- Adhesives

### SAFETY AND HANDLING

This latex may contain traces of residual monomers, which may be released during processing at high temperatures. Adequate ventilation should be employed in the processing areas.

Please read the material safety data sheet (MSDS) prior to use. Copy can be obtained by contacting your Customer Service Representative.

### PACKAGING, STORAGE AND SHELF-LIFE

Normal packaging is 200 litres plastic drums (closed head with two bungs). Bulk packaging is available.

Store in original packaging; Store at 41° to 104°F (5° to 40°C). Protect from freezing.

Typical shelf life is 6 months when stored as recommended.

PDS-NL238-17-01

apcotex industries limited

Email  : info@apcotex.com

Web  : www.apcotex.com

**Disclaimer :** These suggestions and data are based on information that we believe to be reliable. They are given for information only and in good faith, but conditions and methods of use of our products are beyond our control. Apcotex recommends that the user determine the suitability of our materials and suggestions before using them on a commercial scale