



Apcoflex[®] NLX530

Anionic aqueous dispersion of a Carboxylated Butadiene-Acrylonitrile copolymer

KEY ADVANTAGES

- Contains non-staining antioxidant
- Excellent Fuel & solvent Resistance
- Excellent gloss development, moderate tackiness
- High chemical stability and low fuel foam
- High oil resistance
- Cross-linkable with various reactive groups
- Use of curing agents and accelerators can improve film strength

APPLICATIONS

- Nitrile based adhesives, rubber bladders and brake pads
- Paper saturant: Masking tapes to abrasive papers

PRODUCT SPECIFICATIONS

PROPERTY	LIMITS
pH	8.0 –10.0
Total solids, %	48.0–52.0
Brookfield Viscosity, cps	120 max.
Bound Acrylonitrile, %	28 – 34

SAFETY AND HANDLING

This Latex may contain traces of residual monomers, which may be released during processing at high temperatures. Adequate ventilation should be employed in the processing areas.

Please read the material safety data sheet (MSDS) prior to use. Copy can be obtained by contacting your Customer Service Representative.

PACKAGING, STORAGE AND SHELF-LIFE

Normal packaging is 200 litres plastic drums (closed head with two bungs). Bulk packaging is available.

Store in original packaging. Store at 41° to 104°F (5° to 40°C). Protect from freezing.

Typical shelf life is 6 months when stored as recommended

PDS-NLX 530-18-09

apcotex industries limited

Email  : info@apcotex.com

Web  : www.apcotex.com

Disclaimer : These suggestions and data are based on information that we believe to be reliable. They are given for information only and in good faith, but conditions and methods of use of our products are beyond our control. Apcotex recommends that the user determine the suitability of our materials and suggestions before using them on a commercial scale