



## Apcoflex<sup>®</sup> P615C

### Powdered NBR Rubber

#### CHEMICAL DESCRIPTION

Apcoflex<sup>®</sup> P615C is a medium acrylonitrile, medium Mooney Viscosity linear rubber in powdered form

CAS N°: 9003-18-3

#### APPLICATIONS

Apcoflex<sup>®</sup> P615C is specially suitable for footwear, Molded goods and for the modification of plasticised PVC in extruded profiles.

The other major applications of P615 is in the manufacture of Nitrile based adhesives, Friction materials etc.

#### SAFETY AND HANDLING

Apcoflex<sup>®</sup> P615C may contain traces of residual monomers, which may be released during processing at high temperatures. Therefore adequate ventilation should be employed in the processing areas

#### PRODUCT SPECIFICATIONS

PROPERTY	LIMITS
Volatile Matter,%	0.7 Max.
Mooney Viscosity, ML 1+4 @ 100°C, MU	50 - 60
Ash Content,%	5.0 – 9.0
Bound Acrylonitrile (Polymer), %	32 - 35

#### PACKAGING AND SHELF-LIFE

The powder is packed in plastic bags and is placed in plastic coated multiply cardboard boxes. The boxes are then put on Wooden Crates and shrink wrapped for easy transportation and handling.

Unit: 25 Kg / 55 lb Poly-bags

Bulk: Wooden Pallet 36 units 900 Kg / 1984 lb

20' FCL: 12 pallets 10,800 Kg / 23,810 lb

Recommended to store in original packaging, away from direct sources of heat and sunlight. These powders will have a minimum of 12 months shelf-life from date of manufacture, if good storage practices are maintained. However, they have a tendency to agglomerate over a period of six months

PDS-P615C-18-09

apcotex industries limited

Email  : info@apcotex.com

Web  : www.apcotex.com

**Disclaimer :** These suggestions and data are based on information that we believe to be reliable. They are given for information only and in good faith, but conditions and methods of use of our products are beyond our control. Apcotex recommends that the user determine the suitability of our materials and suggestions before using them on a commercial scale