



CHEMICAL DESCRIPTION

Apcoflex[®] NVC255E* is a blend of Apcoflex low NBR and PVC in the ratio 50:50.

It contains non-staining stabilizer and comes in light tan coloured sheet form.

CAS No.: 9003-18-3 : NBR

CAS No.: 9002-86-2 : PVC

APPLICATIONS

Apcoflex[®] NVC255E is a Very high viscosity polyblend of Nitrile Rubber and PVC in the ratio 50:50 designed for low temperature application. It provides Oil, Fuel, thermal resistance as well as Ozone and environmental resistance.

It is recommended for the manufacture of extruded and molded products suitable for out-door applications in automotive and industrial applications.

This is cost effective, low ACN blend for general purpose automotive and industrial moulded and extruded products.

***E grades are free from DOP and heavy metals.**

PRODUCT SPECIFICATIONS

CHARACTERISTICS	LIMITS
Volatile Matter, %	0.7 Max
Mooney Viscosity, ML ₁₊₄ @ 100°C, MU	70 - 85
Ash Content, %	1.0 Max

SAFETY AND HANDLING

Recommended to store in original packaging, away from direct sources of heat and sunlight. These Polyblends will have a minimum of 24 months shelf-life under good storage practices.

PACKAGING AND SHELF-LIFE

These NVC sheets are wrapped in LDPE films and are then packed in woven sacks.

Appx. Dimensions (in):
30x 16x 5 (when packed)

Weight, 35 kg net (when packed)

Recommended to store in original packaging, away from direct sources of heat and sunlight. These Polyblends will have a maximum of 24 months shelf-life from the date of manufacture when stored at temperature not exceeding 35°C.

For further information, call + 91 22277 70800

PDS - NVC255E - 2023 - 00

Apcotex Industries Limited

info@apcotex.com

www.apcotex.com

Plant 1

Taloja – Plot No.3/1, MIDC
Industrial Area, Taloja-410208

Plant 2

Valia - Village Dungri,
Taluka-Valia, Ankleshwar-393135

Disclaimer : These suggestions and data are based on the information that we believe to be reliable. They are given for the information only and in good faith, but conditions and methods of use of our product are beyond our control. Apcotex recommends that the user determine the suitability of our material and suggestions before using them for a commercial scale.