

CHEMICAL DESCRIPTION

Apcotex TSN651 is a specialty Styrene Butadiene Latex used as an admixture in cement mortar and concrete.

It is manufactured by employing state-of-the-art emulsion polymerization technology ensuring product consistency.

APPLICATIONS/ADVANTAGES

- Bonding agent, cementitious waterproofing, repair mortar.
- Provides excellent water impermeability, bonding.
- Offers good workability at reduced water/ cement ratio.
- Improved bonding and adhesion to substrates.
- Improved toughness and flexibility.
- Mixes can be applied in thinner sections.

SAFETY AND HANDLING

General safety precautions such as goggles, gloves and face shields should be used while handling. (Refer MSDS for detail information)

PRODUCT SPECIFICATIONS

Appearance	Milky white pourable liquid
Emulsifying System	Synthetic anionic and nonionic
Total Solids (%)	51.0 <u>+</u> 1.0
pH at 25°C	9.5 ± 0.5
Brookfield Viscosity LVF (CPS) SP.1, 12 RPM at 25°C	50 - 250
Surface Tension (Dynes/cm) at 25°C	40 ± 5.0
Specific Gravity	1.023 ± 0.005
Dilutability with water	Dilutable in any proportion
Compatibility	Compatible with Cement and Concrete mixture

STORAGE RECOMMENDATIONS

- Store between temperatures of + 5°C and 40°C.
- Keep containers closed when not in use.
- Shelf-life: Six months from the date of manufacturing provided stored under shade, away from direct heat and sunlight, and well protected from freezing.
- Packing: 200/100/50 Kg HDPE Drums.

For further information, call + 91 22277 70800

PDS - TSN651 - 2023 - 00

Apcotex Industries Limited info@apcotex.com www.apcotex.com

Taloja – Plot No.3/1, MIDC Industrial Area, Taloja-410208 Plant 2 Valia - Village Dungri, Taluka-Valia, Ankleshwar-393135

Disclaimer: These suggestions and data are based on the information that we believe to be reliable. They are given for the information only and in good faith, but conditions and methods of use of our product are beyond our control. Apcotex recommends that the user determine the suitability of our material and suggestions before using them for a commercial scale.