Apcotex TY100



CHEMICAL DESCRIPTION

Apcotex TY100 is a copolymer of styrene butadiene latex used for dipping of fabric for tyre cord, V-belts and conveyor belts. Its application also includes textile finishing and adhesive.

It is manufactured by emulsion polymerization method with state-of-the-art manufacturing facilities to produce consistent product.

ADVANTAGES

- Excellent Mechanical stability and chemical stability.
- Compatible with vinyl pyridine latex.
- Aids in processing.
- Excellent gloss development and good wet pick resistance.
- Good tackiness properties.
- Provide excellent film strength.

PRODUCT SPECIFICATIONS

Appearance	Off white liquid
Emulsifying System	Synthetic anionic
Total Solids (%)	41.0 ± 1.0
pH at 25°C	11.0 <u>+</u> 1.0
Brookfield Viscosity LVF (CPS) SP.1, 60 RPM at 25°C	40.0 <u>+</u> 20.0
Surface Tension (Dynes/cm) at 25°C	59 <u>+</u> 5.0
Coagulum (%)	0.05 Max
Mechanical stability (g/100cc)	0.3 Max
ML ₁₊₄ @ 100°C (ASTM D1417)	90 Max

SAFETY AND HANDLING

 General safety precautions such as goggles, gloves and face shields should be used while handling. (Refer MSDS for detail information)

STORAGE RECOMMENDATION

- Store between temperatures of + 5°C and 40°C.
- Keep containers closed when not in use.
- Shelf-life: Six months from the date of manufacturing provided stored under shade, away from direct heat and sunlight, and well protected from freezing.

For further information, call + 91 22277 70800

Apcotex Industries Limited info@apcotex.com www.apcotex.com **Plant 1** Taloja – Plot No.3/1, MIDC Industrial Area, Taloja-410208 **Plant 2** Valia - Village Dungri, Taluka-Valia, Ankleshwar-393135

PDS TY100 - 2023 - 00

Disclaimer : These suggestions and data are based on the information that we believe to be reliable. They are given for the information only and in good faith, but conditions and methods of use of our product are beyond our control. Apcotex recommends that the user determine the suitability of our material and suggestions before using them for a commercial scale.