



CHEMICAL DESCRIPTION

Apcotex CB 620 is an APEO free Carboxylated Styrene-Butadiene Latex designed for its high mechanical stability makes it suitable for spraying (e.g. binding of non-woven fabrics). It can also be utilized for full bath impregnation of needle felt, and for application from a lick roller trough.

It is manufactured by employing state-of-the-art emulsion polymerization technology ensuring product consistency.

APCOTEX CB 620 is capable, without the addition of extra surface active agents, of being foamed up to very light cup weights.

APPLICATIONS/ADVANTAGES

- Excellent high mechanical stability.
- Low roller deposit and easily sprayable.
- Good wet delamination strength.
- Low VOC and odour.
- Good viscosity stability with normal Acrylate thickener.

SAFETY AND HANDLING

General safety precautions such as goggles, gloves and face shields should be used while handling. (Refer MSDS for detail information)

PRODUCT SPECIFICATIONS

Appearance	Milky white pourable liquid
Emulsifying System	Synthetic anionic
Total Solids (%)	50.0 ± 1.0
pH at 25°C	7.0 ± 1.0
Brookfield Viscosity LVF (CPS) SP.1, 12 RPM at 25°C	100 - 500
Surface Tension (Dynes/cm) at 25°C	40.0 ± 5.0
Compatibility with fillers	Excellent
Bactericide	Present
Antioxidant	Present

STORAGE RECOMMENDATIONS

- Store between temperatures of + 5°C and 40°C.
- Keep containers closed when not in use.
- Shelf-life: Six months from the date of manufacturing provided stored under shade, away from direct heat and sunlight, and well protected from freezing.
- Packing: Flexi/200 Kg HDPE Drums.

For further information, call + 91 22277 70800

PDS – CB620 - 2020 - 02

Apcotex Industries Limited
info@apcotex.com
www.apcotex.com

Plant 1
Taloja – Plot No.3/1, MIDC
Industrial Area, Taloja-410208

Plant 2
Valia - Village Dungri,
Taluka-Valia, Ankleshwar-393135

Disclaimer : These suggestions and data are based on the information that we believe to be reliable. They are given for the information only and in good faith, but conditions and methods of use of our product are beyond our control. Apcotex recommends that the user determine the suitability of our material and suggestions before using them for a commercial scale.