



## CHEMICAL DESCRIPTION

Inzapol TX 6300 is self-cross-linking Styrene Butadiene Acrylonitrile copolymer latex.

It is manufactured by employing state-of-the-art emulsion polymerization technology ensuring product consistency.

## APPLICATIONS/ADVANTAGES

- Self-crosslinking polymer for high efficient roofing felt application.
- Cross-linked film is very hard and brittle at room temperature.
- High resistance to acids and alkali.
- Reinforcement of non-woven fabric for grinding application.
- High efficient roofing felt application.

## SAFETY AND HANDLING

General safety precautions such as goggles, gloves and face shields should be used while handling. (Refer MSDS for detail information)

## PRODUCT SPECIFICATIONS

Appearance	Milky white pourable liquid
Emulsifying System	Synthetic anionic
Total Solids (%)	40.0 ± 0.5
pH at 25°C	7.5 ± 0.5
Brookfield Viscosity LVF (CPS) SP.1, 12 RPM at 25°C	100 Max
Surface Tension (Dynes/cm) at 25°C	40 ± 3.0
Film Characteristics	Clear
Bactericide	Present
Antioxidant	Present

## STORAGE RECOMMENDATIONS

- Store between temperatures of + 5°C and 40°C.
- Keep containers closed when not in use.
- Shelf-life: Six months from the date of manufacturing provided stored under shade, away from direct heat and sunlight, and well protected from freezing.
- Packing: Flexi/IBC/200 Kg HDPE Drums.

For further information, call + 91 22277 70800

PDS - TX 6300 - 2023 - 00

**Apcotex Industries Limited**  
info@apcotex.com  
www.apcotex.com

**Plant 1**  
Taloja – Plot No.3/1, MIDC  
Industrial Area, Taloja-410208

**Plant 2**  
Valia - Village Dungri,  
Taluka-Valia, Ankleshwar-393135

**Disclaimer** : These suggestions and data are based on the information that we believe to be reliable. They are given for the information only and in good faith, but conditions and methods of use of our product are beyond our control. Apcotex recommends that the user determine the suitability of our material and suggestions before using them for a commercial scale.