



### CHEMICAL DESCRIPTION

Apcotex TSN700 is Carboxylated Styrene-Butadiene Latex used for modification of hydraulic binders. The dispersion is free from plasticizers and film forming aids.

It is manufactured by employing state-of-the-art emulsion polymerization technology ensuring product consistency.

### APPLICATIONS/ADVANTAGES

- Hydraulic cement admixture, flexible cementitious waterproofing coatings, oil well cementing.
- High resistance to alkaline hydrolysis.
- Provides excellent water impermeability and chemical resistance.
- Excellent workability at reduced water/cement ratio.
- Improved bonding and adhesion to substrates.
- Longer pot life for polymer-cement mix.
- Provides balanced toughness and flexibility.

### SAFETY AND HANDLING

General safety precautions such as goggles, gloves and face shields should be used while handling. (Refer MSDS for detail information)

### PRODUCT SPECIFICATIONS

Appearance	Milky white pourable liquid
Emulsifying System	Synthetic anionic and nonionic
Total Solids (%)	47.0 ± 1.0
pH at 25°C	10.5 ± 0.5
Brookfield Viscosity LVF (CPS) SP.1, 12 RPM at 25°C	100 - 250
Surface Tension (Dynes/cm) at 25°C	40 ± 5.0
Specific Gravity	1.020 ± 0.005
Dilutability with water	Dilutable in any proportion

### STORAGE RECOMMENDATIONS

- Store between temperatures of + 5°C and 40°C.
- Keep containers closed when not in use.
- Shelf-life: Six months from the date of manufacturing provided stored under shade, away from direct heat and sunlight, and well protected from freezing.
- Packing: IBC and 200 Kg Kg HDPE Drums.

For further information, call + 91 22277 70800

PDS - TSN700 - 2023 - 00

**Apcotex Industries Limited**  
info@apcotex.com  
www.apcotex.com

**Plant 1**  
Taloja – Plot No.3/1, MIDC  
Industrial Area, Taloja-410208

**Plant 2**  
Valia - Village Dungri,  
Taluka-Valia, Ankleshwar-393135

**Disclaimer :** These suggestions and data are based on the information that we believe to be reliable. They are given for the information only and in good faith, but conditions and methods of use of our product are beyond our control. Apcotex recommends that the user determine the suitability of our material and suggestions before using them for a commercial scale.